



# Lidding Films

## TYPICAL PROPERTIES OF LWMP - White Multi-Purpose Lidding Film

<b>Purpose</b>	A medium barrier, white, peelable lidding film designed to adhere to multiple substrates.
<b>Features</b>	<ul style="list-style-type: none"> <li>• Medium moisture and oxygen barrier</li> <li>• Strong, durable film</li> <li>• Printable</li> <li>• Great for fresh or frozen foods</li> <li>• Optimal sealing temperature of 375 °F</li> </ul>

Properties		Units	Value
Thickness		Gauge	.002"
Yield		in <sup>2</sup> / lb	12,900
Water Vapor Transmission Rate		gms / 100 sq. in. / 24 hours @ 38° C	0.5
Oxygen Transmission Rate		cm <sup>3</sup> / 100 sq. in. / 24 hours @ 23° C	6
Tensile strength at break	MD	lb/in <sup>2</sup>	9,000
	TD		9,500
Elongation at break	MD	%	100
	TD		100
COF	Sealant Side		<0.4
	Heat resistant Side		0.5
Vicat Softening Temperature		°F	220

Please note: It is the responsibility of our customers to determine that their use of our product(s) is safe, lawful, and suitable in their intended end use applications.

**Storage & Handling:** Lidding Films should be placed in the processing area 24 hours prior to processing to acclimatize. Even though these films are largely unaffected by climatic conditions, they should not be stored at temperatures above 104 degrees F. Under suitable storage conditions, the film can be stored for a period of six months without any risk of deterioration.

*The information herein, is to the best of our knowledge, true, and accurate. However, since conditions of use are beyond our control, all recommendations or suggestions are presented without guarantee or responsibility on our part.*

January 2016